



# CORAL HiPIMS

## AlTiSiN

# CORAL HiPIMS



Coral is the new AlTiSiN coating, deposited with HiPIMS technology and developed to improve the carbide cutting tools performances when machining of medium and high strength steels. The HiPIMS technology ensures excellent coating roughness, high toughness, hardness and wear resistance which allow to reduce machining time and to obtain better surface finish.

## MAIN APPLICATION

- Machining of medium and high strength steels with carbide cutting tools
- Micro tools for drilling and milling

## COATING PROPERTIES

### VISUAL FEATURES

#### Surface



Values	Measurement parameters of color According to ISO11664-4
$50 \pm 1$	L* Brightness
$7.5 \pm 1$	a* Color coordinate
$7 \pm 1$	b* Color coordinate

#### NOTES:

Non-functional requirement; indicative values

### PHYSICAL FEATURES

Measure	Values	Measurement
Coating thickness*	$1.5 \pm 4 \mu\text{m}$	Calotest on sample
Coating hardness***	$3100 \pm 200 \text{ HV}$	Nanoindentation 20mN/20s
Roughness Ra**	0.080 $\mu\text{m}$	From sample with Ra < 0,03 $\mu\text{m}$
Coefficient of friction**	$0.55 \pm 0.1$	Pin on disk, dry, against $\text{Al}_2\text{O}_3$

#### NOTES:

- \* depends on the application.
- \*\* depends on the test conditions.

### TECHNOLOGICAL FEATURES

Coating technology	HiPIMS
Chemical composition	AlTiSiN
Structure	Multilayer
Coating temperature	450°C
Maximum working temperature	1100°C
Biocompatibility	-
Food compatibility	-